

# Characteristics of Material



冠磁企業股份有限公司  
CROWN FERRITE ENTERPRISE CO.  
TEL:886-2-2633-1155 FAX:886-2-2633-4214  
<http://www.cfe.com.tw> e-mail:crownco@cfe.com.tw

## Material L92

$\mu_i$	$\tan \delta / \mu_i$	$\alpha m r$	Bm	Br	Hc	Tc	$r$	d
-	$\times 10^{-6}$	$\times 10^{-6} / ^\circ C$	Gauss	Gauss	Oersted	$^\circ C$	$\Omega - cm$	$g / cm^3$
1500	7(0.05MHz) 70(1.5MHz)	2	2700	1100	0.2	150	$10^7$	4.8

