

# Characteristics of Material



冠磁企業股份有限公司  
 CROWN FERRITE ENTERPRISE CO.  
 TEL:886-2-2633-1155 FAX:886-2-2633-4214  
<http://www.cfe.com.tw> e-mail:crownco@cfe.com.tw

## Material M8

$\mu_i$	$\tan d / \mu_i$	$amr$	Bm	Br	Hc	Tc	$r$	d
-	$\times 10^{-6}$	$\times 10^{-6} / ^\circ C$	Gauss	Gauss	Oersted	$^\circ C$	$\Omega - cm$	$g / cm^3$
50	200(0.5MHz) 900(40MHz)	45	3400	1900	6.2	300	$10^6$	4.8

