

Characteristics of Material



冠磁企業股份有限公司
 CROWN FERRITE ENTERPRISE CO.
 TEL:886-2-2633-1155 FAX:886-2-2633-4214
<http://www.cfe.com.tw> e-mail:crownco@cfe.com.tw

Material V2M

μ_i	$\tan d / \mu_i$	$\alpha_{\mu r}$	Bm	Br	Hc	Tc	r	d
-	$\times 10^{-6}$	$\times 10^{-6} / ^\circ C$	Gauss	Gauss	Oersted	$^\circ C$	$\Omega - cm$	g / cm^3
40	140(2MHz) 1500(60MHz)	40	3300	2000	6	300	10^6	4.8

